

## JV5300

### Self Adhesive Vinyl With Clear Removable Adhesive

#### Description:

Film: 100 micron; glossy PVC film  
 Adhesive: Clear removable adhesive  
 Liner: 140 gsm white PEK paper with one side PE & Silicon coating  
 Width: 1.06/1.27/1.37/1.52/1.82/2.02m

#### Features:

1. Excellent printability and handling.
2. The adhesive force value is light, suitable for glass, acrylic plate and other smooth surface.
3. Good dimensional stability after application.
4. Easy application to a wide variety of substrates.

#### Applications:

1. Applicable to Vehicle Wrapping Media, Billboards, indoor and outdoor advertising
2. Suitable for various solvent ink, Eco-solvent ink and UV ink

#### Technical Data:

Testing condition: Indoor temperature 23±2°C; Relative humidity 50±5%; Use aluminum, glass, steel plate as the base material for testing.

Test Items	Units	Test method	Average value
Thickness PVC	Micron	GB/T6672-2001	100±10
Weight-Liner	g/m <sup>2</sup>	GB4669-1995	140±10
Weight -finished product	g/m <sup>2</sup>	GB4669-1995	300±20
Gloss Rate 60°	%	GB8807-88	≥60
Initial Adhesion	N/25mm	FTM 9	≥3
24h, 180° peel	N/25mm	FTM 1	≥4
Dimensional stability MD	mm	FTM 14	≤1.2
Dimensional stability CD	mm	FTM 14	≤1.0
Tensile strength MD	N/25 mm	GB/T1040.1-2006	≥45
Tensile strength CD	N/25 mm	GB/T1040.1-2006	≥40
Construction Temperature	°C		20±10°C
Applicable Temperature	°C		-20 ~ +70°C

● All technical data is subject to change without prior notice.

#### Storage Condition:

All JANEHONG products always need to be stored in the original packing and with the original protection materials, preferably stored hermetically, no more than 6 layers if stored horizontally. Do not expose in direct sunlight or heat sources. Shelf life will be one year with temperature of 25°C±5°C and relative humidity of 50±15%.

#### Production and Application Environment:

Production environment: temperature of 25±5°C, relative humidity of 50%±10%, clean dust-free environment without suspended matter; Please move the materials to the printing environment 24 hours before printing. Test prior to use and remain enough edge margins when printing.

Application environment: temperature of 20±10°C, relative humidity of 50±10%; Pasting on flat, smooth and clean surface without floating dust and shedding; It is necessary to take more than 2 hours for maintenance before laminating.

#### Warranty Condition:

1. One year shelf life: stored in suitable conditions, preferably use within six months.
2. One year prosecution period: from the product manufacture date, no-acceptance for overdue product.

#### Important Remark:

1. The information mentioned in this product data sheet is based upon tests that were executed by JANEHONG, and that we consider to be reliable. Environment humidity more than 70% in different district will decrease the printing result.
2. This SAV product is with removable glue and can guarantee the remove performance within 1 year if on the paint plate and smooth surface. Advise to use the same batch product to joint.

#### Product Application:

